

150ml Glass Syringe

with 3/8" UNF Threaded Nut



Tomopal Part # 140-8150

Piston Outside Diameter: $34.20 \text{ mm} \pm 0.25 \text{ mm}$ D1) Barrel Diameter Outside: $39.60 \text{ mm} \pm 0.75 \text{ mm}$ D2) Barrel Collar Diameter: $52.00 \text{ mm} \pm 0.75 \text{ mm}$ D3) Piston Collar Diameter: $42.00 \text{ mm} \pm 0.65 \text{ mm}$ L) Length: $281.50 \text{ mm} \pm 0.65 \text{ mm}$

Increment: 5.0 ml

Volume: 150.0 ml \pm 1.5% of volume

Features:

- The syringe is made from heat resistant borosilicate glass.
- The material and construction is resistant to breakage from shock and sudden temperature changes.
- · It is annealed and tested until free of internal strain, to withstand repeated washing with hot water.
- Reinforced at 3/8" UNF threaded tip and barrel base, the points at which most breakage occurs.
- The cylinder-plunger fit is leak proof and meets the requirements of Federal Specification GG -S- 921b.
- Plunger is individually ground and fitted to barrel for smooth movement with no back flow.
- · Barrel rim is flat on both sides to prevent rolling and is wide enough for convenient finger tip grip.
- The syringes are available in custom fit design. The custom fit syringes are uniquely numbered for matching piston and barrel.
- The 3/8" UNF threaded nut fitting is made from stainless steel or chrome-plated brass.
- The syringe is clearly marked with graduations of 5.0 ml and 10 ml. The graduations are permanently fused for lifetime legibility.

Color:

Glass Properties:

Expansion coefficient:52 +/- 10-7 / CentigradeDensity:2.36g +/- 0.03g CM³Modulus of elasticity:64 +/- 10³ mm⁻²Water resistance:First ClassAcid resistance:First ClassAlkali resistance:First Class

Softening point:785 @ degrees centigradeMelting temperature:1260 @ degrees centigradeStrain point:525 @ degrees centigradeAnnealing point:570 @ degrees centigradeHardness:7

Clear

Tel: 916.429.7240 Fax: 916.429.2701